

In the Claims:

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

1. (Currently amended) A liquid crystal display comprising:

a liquid crystal panel having an upper plate, a lower plate and liquid crystal injected between the upper plate and the lower plate;

a polarizing plate disposed on the liquid crystal panel; and

an optical film containing a phase difference film and a linear polarizer contacting the phase difference film,

wherein the phase difference film and the linear polarizer contacting the phase difference film transmit light to the liquid crystal panel, the linear polarizer has a light transmittance axis perpendicular to a light transmittance axis of the polarizing plate, and the optical film is positioned at a bottom surface of the liquid crystal panel, and the linear polarizer is disposed between the liquid crystal panel and the phase difference film.

2. (Currently amended) A coating type optical film comprising:

a circular polarizer containing cholesteric liquid crystal;

an adhesive layer formed on the circular polarizer;

a phase difference film formed on the adhesive layer; and

a linear polarizer directly coated on the phase difference film,

wherein the linear polarizer directly coated on the phase difference film transmits light from the circular polarizer to a liquid crystal panel.

3. (Original) The coating type optical film according to claim 2, further comprising a compensation film formed between the phase difference film and the circular polarizer.

4. (Original) The coating type optical film according to claim 2, wherein the linear polarizer comprises a lyotropic liquid crystal.

5. (Original) The coating type optical film according to claim 4, wherein the lyotropic liquid crystal contains dye or pigment.

6. (Original) The coating type optical film according to claim 2, wherein the optical film has a thickness of at most about 200 μm .

7. (Original) The coating type optical film according to claim 2, wherein the linear polarizer has a thickness of a few μm .

8. (Withdrawn) A coating type optical film comprising:

an interference type linear polarizer; and

a linear polarizer directly coated on the interference type linear polarizer.

9. (Withdrawn) The coating type optical film according to claim 8, wherein the linear polarizer comprises a lyotropic liquid crystal.

10. (Withdrawn) The coating type optical film according to claim 9, wherein the lyotropic liquid crystal contains dye or pigment.

11. (Withdrawn) The coating type optical film according to claim 8, wherein the optical film has a thickness of at most about 200 μm .

12. (Withdrawn) The coating type optical film according to claim 8, wherein the linear polarizer has a thickness of a few μm .

13. (Currently amended) A method for fabricating a coating type optical film, comprising:

(a) forming a circular polarizer containing cholesteric liquid crystal on a transparent substrate;

(b) forming an adhesive layer on the circular polarizer;

(c) forming a phase difference film on the adhesive layer; and

(d) forming a linear polarizer by directly coating liquid crystal on the phase difference film,

wherein the linear polarizer formed by directly coating the liquid crystal on the phase difference film transmits light from the circular polarizer to a liquid crystal panel.

14. (Original) The method according to claim 13, further comprising:

(e) after (b), forming a compensation film; and

(f) forming another adhesive layer on the compensation film.

15. (Original) The method according to claim 13, wherein the liquid crystal is coated by a method selected from the group consisting of a bar coating method, a knife coating method and a slit-die coating method.

16. (Original) The method according to claim 13, wherein the coated liquid crystal comprises a lyotropic liquid crystal.

17. (Original) The method according to claim 16, wherein the lyotropic liquid crystal contains dye or pigment.

18. (Original) The method according to claim 13, wherein the linear polarizer has an E-mode polarization.

19. (Original) The method according to claim 13, wherein the optical film has a thickness of at most about 200 μm .

20. (Original) The method according to claim 13, wherein the linear polarizer has a thickness of a few μm .

21. (Withdrawn) A method for fabricating a coating type optical film, comprising:

(a) preparing an interference type linear polarizer; and

(b) forming a linear polarizer by directly coating liquid crystal on the interference type linear polarizer.

22. (Withdrawn) The method according to claim 21, wherein the liquid crystal is coated by a method selected from the group consisting of a bar coating method, a knife coating method and a slit-die coating method.

23. (Withdrawn) The method according to claim 21, wherein the coated liquid crystal comprises a lyotropic liquid crystal.

24. (Withdrawn) The method according to claim 23, wherein the lyotropic liquid crystal includes dye or pigment.

25. (Withdrawn) The method according to claim 21, wherein the linear polarizer has an E-mode polarization.

26. (Withdrawn) The method according to claim 21, wherein the optical film has a thickness of at most about 200 μm .

27. (Withdrawn) The method according to claim 21, wherein the linear polarizer has a thickness of a few μm .

28. (Withdrawn) A coating type optical film comprising:

a circular polarizer containing cholesteric liquid crystal;

an adhesive layer formed on the circular polarizer;

a phase difference film formed on the adhesive layer; and

a linear polarizer directly coated on a substrate adhered to a top of the phase difference film.

29. (Withdrawn) The coating type optical film according to claim 28, wherein the linear polarizer comprises a lyotropic liquid crystal.

30. (Withdrawn) The coating type optical film according to claim 29, wherein the lyotropic liquid crystal contains dye or pigment.

31. (Withdrawn) The coating type optical film according to claim 28, wherein the optical film has a thickness of at most about 200 μm .

32. (Withdrawn) The coating type optical film according to claim 28, wherein the linear polarizer has a thickness of a few μm .

33. (Withdrawn) A coating type optical film comprising:

an interference type linear polarizer; and

a linear polarizer directly coated on a substrate adhered to a top of the interference type linear polarizer.

34. (Withdrawn) The coating type optical film according to claim 33, wherein the linear polarizer comprises a lyotropic liquid crystal.

35. (Withdrawn) The coating type optical film according to claim 34, wherein the lyotropic liquid crystal contains dye or pigment.

36. (Withdrawn) The coating type optical film according to claim 33, wherein the optical film has a thickness of at most about 200 μm .

37. (Withdrawn) The coating type optical film according to claim 33, wherein the linear polarizer has a thickness of a few μm .